


D50=1.95+_0.20 Date: 11/11/22 Meas #: N/A
 Time: 11:16 Pres #: N/A

HENAN YALONG SUPERHARO MATERIALS CO;LTD
 16-5A NO.43 ZHONGYUAN WEST ROAD
 ZHENG ZHOU P.C.450007 CHINA
 TEL:86-371-67650359
 FAX:86-371-67650319

Summary	Percentiles	Dia	Vol%	Width	
mv = 2.028	5% = 1.091	60% = 2.119	1.965	100%	1.226
mn = 1.462	10% = 1.250	70% = 2.291			
ma = 1.827	30% = 1.656	80% = 2.510			
cs = 3.284	40% = 1.813	90% = 2.848			
sd = 0.613	50% = 1.965	95% = 3.189			



SIZE	%PASS	%CHAN	SIZE	%PASS	%CHAN	SIZE	%PASS	%CHAN	SIZE	%PASS	%CHAN
704.0	100.00	0.00	80.70	100.00	0.00	9.250	100.00	0.00	1.060	4.21	1.82
645.6	100.00	0.00	74.00	100.00	0.00	8.482	100.00	0.00	0.972	2.39	1.15
592.0	100.00	0.00	67.86	100.00	0.00	7.778	100.00	0.00	0.892	1.24	0.69
542.9	100.00	0.00	62.23	100.00	0.00	7.133	100.00	0.00	0.818	0.55	0.38
497.8	100.00	0.00	57.06	100.00	0.00	6.541	100.00	0.00	0.750	0.17	0.17
456.5	100.00	0.00	52.33	100.00	0.00	5.998	100.00	0.00	0.688	0.00	0.00
418.6	100.00	0.00	47.98	100.00	0.00	5.500	100.00	0.13	0.630	0.00	0.00
383.9	100.00	0.00	44.00	100.00	0.00	5.044	99.87	0.23	0.578	0.00	0.00
352.0	100.00	0.00	40.35	100.00	0.00	4.625	99.64	0.36	0.530	0.00	0.00
322.8	100.00	0.00	37.00	100.00	0.00	4.241	99.28	0.60	0.486	0.00	0.00
296.0	100.00	0.00	33.93	100.00	0.00	3.889	98.68	1.04	0.446	0.00	0.00
271.4	100.00	0.00	31.11	100.00	0.00	3.566	97.64	1.83	0.409	0.00	0.00
248.9	100.00	0.00	28.53	100.00	0.00	3.270	95.81	3.10	0.375	0.00	0.00
228.2	100.00	0.00	26.16	100.00	0.00	2.999	92.71	4.89	0.344	0.00	0.00
209.3	100.00	0.00	23.99	100.00	0.00	2.750	87.82	7.31	0.315	0.00	0.00
191.9	100.00	0.00	22.00	100.00	0.00	2.522	80.51	9.36	0.289	0.00	0.00
176.0	100.00	0.00	20.17	100.00	0.00	2.312	71.15	11.03	0.265	0.00	0.00
161.4	100.00	0.00	18.50	100.00	0.00	2.121	60.12	11.47	0.243	0.00	0.00
148.0	100.00	0.00	16.96	100.00	0.00	1.945	48.65	10.62	0.223	0.00	0.00
135.7	100.00	0.00	15.56	100.00	0.00	1.783	38.03	9.32	0.204	0.00	0.00
124.5	100.00	0.00	14.27	100.00	0.00	1.635	28.71	7.57	0.187	0.00	0.00
114.1	100.00	0.00	13.08	100.00	0.00	1.499	21.14	6.03	0.172	0.00	0.00
104.7	100.00	0.00	12.00	100.00	0.00	1.375	15.11	4.71	0.158	0.00	0.00
95.96	100.00	0.00	11.00	100.00	0.00	1.261	10.40	3.57	0.145	0.00	0.00
88.00	100.00	0.00	10.09	100.00	0.00	1.156	6.83	2.62	0.133	0.00	0.00

Distribution: Volume	RunTime: 10 seconds	Fluid: Water
Progression: Geometric Root8	Run Number 1 of 1 runs	Fluid Refractive Index: 1.33
Upper Edge: 704.0	Particle: W 0.5	Loading Factor: 0.0211
Lower Edge: 0.122	Particle Transparency: Trans	Transmission: 0.93
Residuals: Disabled	Particle Refractive Index: 2.41	Above Residual: 0.00
Number Of Channels: 100	Particle Shape: Irregular	Below Residual: 0.00
X100 Extended Range: No		
Filter: On	Database Path: N/A	Efficiency Shift: -4.00
		Function Shift: 2.02