


测量详细信息	
Sample Name	Average of '0 -0.5 2072 码'

测量详细信息	
Measurement Date Time	2020/3/27 20:32:48
Result Source	Averaged

分析	
Particle Name	Diamond
Particle Refractive Index	2.418
Particle Absorption Index	0.010
Dispersant Name	Water
Dispersant Refractive Index	1.330
Scattering Model	Mie
Analysis Model	General Purpose
Weighted Residual	0.88 %
Laser Obscuration	9.96 %

结果	
Concentration	0.0004 %
Span	1.840
Uniformity	0.578
Specific Surface Area	28050 m <sup>2</sup> /kg
D [3,2]	0.214 μm
D [4,3]	0.307 μm
Dv (10)	0.119 μm
Dv (50)	0.246 μm
Dv (90)	0.572 μm



Result											
Size ( μm)	% Volume In	Size ( μm)	% Volume In	Size ( μm)	% Volume In	Size ( μm)	% Volume In	Size ( μm)	% Volume In	Size ( μm)	% Volume In
0.0100	0.00	0.0876	2.19	0.767	1.56	6.72	0.00	58.9	0.00	516	0.00
0.0114	0.00	0.0995	3.11	0.872	1.24	7.64	0.00	66.9	0.00	586	0.00
0.0129	0.00	0.113	4.19	0.991	0.91	8.68	0.00	76.0	0.00	666	0.00
0.0147	0.00	0.128	5.36	1.13	0.59	9.86	0.00	86.4	0.00	756	0.00
0.0167	0.00	0.146	6.54	1.28	0.31	11.2	0.00	98.1	0.00	859	0.00
0.0189	0.00	0.166	7.60	1.45	0.12	12.7	0.00	111	0.00	976	0.00
0.0215	0.00	0.188	8.39	1.65	0.00	14.5	0.00	127	0.00	1110	0.00
0.0244	0.00	0.214	8.74	1.88	0.00	16.4	0.00	144	0.00	1260	0.00
0.0278	0.00	0.243	8.59	2.13	0.00	18.7	0.00	163	0.00	1430	0.00
0.0315	0.00	0.276	8.01	2.42	0.00	21.2	0.00	186	0.00	1630	0.00
0.0358	0.00	0.314	7.14	2.75	0.00	24.1	0.00	211	0.00	1850	0.00
0.0407	0.00	0.357	6.06	3.12	0.00	27.4	0.00	240	0.00	2100	0.00
0.0463	0.07	0.405	4.94	3.55	0.00	31.1	0.00	272	0.00	2390	0.00
0.0526	0.21	0.460	3.94	4.03	0.00	35.3	0.00	310	0.00	2710	0.00
0.0597	0.47	0.523	3.08	4.58	0.00	40.1	0.00	352	0.00	3080	0.00
0.0679	0.87	0.594	2.41	5.21	0.00	45.6	0.00	400	0.00	3500	0.00
0.0771	1.44	0.675	1.93	5.92	0.00	51.8	0.00	454	0.00		