


HENAN YALONG SUPERHARO MATERIALS CO;LTD 16-5A NO.43 ZHONGYUAN WEST ROAD ZHENG ZHOU P.C.450007 CHINA TEL:86-371-67650359 FAX:86-371-67650319		D50=13.4+_0.80	Date: 10/13/22 Meas #:N/A Time: 09:53 Pres #: N/A
		Summary	Percentiles
		mv = 14.08	5% = 9.151 60% = 14.28
		mn = 11.72	10% = 9.940 70% = 15.30
		ma = 13.18	30% = 11.85 80% = 16.67
		cs = 0.455	40% = 12.62 90% = 18.93
		sd = 3.387	50% = 13.42 95% = 21.31
			Dia Vol% Width
			13.42 100% 6.775



SIZE	%PASS	%CHAN	SIZE	%PASS	%CHAN	SIZE	%PASS	%CHAN	SIZE	%PASS	%CHAN
704.0	100.00	0.00	80.70	100.00	0.00	9.250	5.44	2.98	1.060	0.00	0.00
645.6	100.00	0.00	74.00	100.00	0.00	8.482	2.46	1.45	0.972	0.00	0.00
592.0	100.00	0.00	67.86	100.00	0.00	7.778	1.01	0.72	0.892	0.00	0.00
542.9	100.00	0.00	62.23	100.00	0.00	7.133	0.29	0.29	0.818	0.00	0.00
497.8	100.00	0.00	57.06	100.00	0.00	6.541	0.00	0.00	0.750	0.00	0.00
456.5	100.00	0.00	52.33	100.00	0.00	5.998	0.00	0.00	0.688	0.00	0.00
418.6	100.00	0.00	47.98	100.00	0.00	5.500	0.00	0.00	0.630	0.00	0.00
383.9	100.00	0.00	44.00	100.00	0.00	5.044	0.00	0.00	0.578	0.00	0.00
352.0	100.00	0.00	40.35	100.00	0.00	4.625	0.00	0.00	0.530	0.00	0.00
322.8	100.00	0.00	37.00	100.00	0.16	4.241	0.00	0.00	0.486	0.00	0.00
296.0	100.00	0.00	33.93	99.84	0.27	3.889	0.00	0.00	0.446	0.00	0.00
271.4	100.00	0.00	31.11	99.57	0.38	3.566	0.00	0.00	0.409	0.00	0.00
248.9	100.00	0.00	28.53	99.19	0.61	3.270	0.00	0.00	0.375	0.00	0.00
228.2	100.00	0.00	26.16	98.58	1.00	2.999	0.00	0.00	0.344	0.00	0.00
209.3	100.00	0.00	23.99	97.58	1.68	2.750	0.00	0.00	0.315	0.00	0.00
191.9	100.00	0.00	22.00	95.90	2.76	2.522	0.00	0.00	0.289	0.00	0.00
176.0	100.00	0.00	20.17	93.14	4.45	2.312	0.00	0.00	0.265	0.00	0.00
161.4	100.00	0.00	18.50	88.69	6.86	2.121	0.00	0.00	0.243	0.00	0.00
148.0	100.00	0.00	16.96	81.83	9.51	1.945	0.00	0.00	0.223	0.00	0.00
135.7	100.00	0.00	15.56	72.32	12.45	1.783	0.00	0.00	0.204	0.00	0.00
124.5	100.00	0.00	14.27	59.87	13.94	1.635	0.00	0.00	0.187	0.00	0.00
114.1	100.00	0.00	13.08	45.93	13.97	1.499	0.00	0.00	0.172	0.00	0.00
104.7	100.00	0.00	12.00	31.96	12.20	1.375	0.00	0.00	0.158	0.00	0.00
95.96	100.00	0.00	11.00	19.76	8.66	1.261	0.00	0.00	0.145	0.00	0.00
88.00	100.00	0.00	10.09	11.10	5.66	1.156	0.00	0.00	0.133	0.00	0.00

Distribution: Volume	RunTime: 10 seconds	Fluid: Water
Progression: Geometric Root8	Run Number 1 of 1 runs	Fluid Refractive Index: 1.33
Upper Edge: 704.0	Particle: W 0.5	Loading Factor: 0.0497
Lower Edge: 0.122	Particle Transparency: Trans	Transmission: 0.96
Residuals: Disabled	Particle Refractive Index: 2.41	Above Residual: 0.00
Number Of Channels: 100	Particle Shape: Irregular	Below Residual: 0.00
X100 Extended Range: No		
Filter: On	Database Path: N/A	Efficiency Shift: -4.00
		Function Shift: 2.02