



百特纳米粒度电位分析仪

体积分布报告页


V4.00

样品名称: M6563-57-1		样品来源: YP	
检测人员:		检测单位: 河南省亚龙超硬材料有限公司	
SOP名称: manual.sop		测试日期: 2024/3/27	测试时间: 11:43
备注: Z-均粒径为真实测量数值, 典型值为模拟数值, 仅供参考			
分散介质: 水	样品材质: 聚苯乙烯乳球	检测角度: 90 °	子测试次数: 15
温度: 25 °C	折射率: 1.59	平均光强: 385.23 kcps	衰减片编号: 4
粘度: 0.8936 mPa.s(cP)	吸收率: 0.01	分析模型: 通用	样品池种类: PS样品池
折射率: 1.33	激光波长: 671 nm	平衡时间: 120 s	检测点位置: 5 mm
测试结果		均径(d.nm)	面积(%)
Z-均粒径: 137.94 nm		峰1 107.56	100.00
PDI: 0.069		峰2	
截距: 0.93		峰3	
		峰标准差(nm)	CV (%)
		31.35	29.15

粒径(d.nm)	区间(%)	累积(%)
0.30	0.00	0.00
0.35	0.00	0.00
0.41	0.00	0.00
0.48	0.00	0.00
0.56	0.00	0.00
0.66	0.00	0.00
0.77	0.00	0.00
0.90	0.00	0.00
1.05	0.00	0.00
1.23	0.00	0.00
1.44	0.00	0.00
1.68	0.00	0.00
1.97	0.00	0.00
2.30	0.00	0.00
2.69	0.00	0.00
3.15	0.00	0.00
3.69	0.00	0.00
4.31	0.00	0.00
5.05	0.00	0.00
5.90	0.00	0.00
6.90	0.00	0.00
8.08	0.00	0.00
9.45	0.00	0.00
11.05	0.00	0.00

粒径(d.nm)	区间(%)	累积(%)
12.93	0.00	0.00
15.12	0.00	0.00
17.69	0.00	0.00
20.69	0.00	0.00
24.21	0.00	0.00
28.32	0.00	0.00
33.12	0.00	0.00
38.75	0.00	0.00
45.33	0.00	0.00
53.02	0.00	0.00
62.02	3.47	3.47
72.55	12.29	15.76
84.87	20.17	35.93
99.28	22.18	58.11
116.13	18.56	76.67
135.85	12.43	89.10
158.91	6.76	95.86
185.89	2.94	98.80
217.45	0.97	99.77
254.37	0.21	99.98
297.55	0.02	100.00
348.07	0.00	100.00
407.16	0.00	100.00
476.29	0.00	100.00

粒径(d.nm)	区间(%)	累积(%)
557.15	0.00	100.00
651.73	0.00	100.00
762.38	0.00	100.00
891.81	0.00	100.00
1043.22	0.00	100.00
1220.32	0.00	100.00
1427.50	0.00	100.00
1669.85	0.00	100.00
1953.34	0.00	100.00
2284.96	0.00	100.00
2672.88	0.00	100.00
3126.66	0.00	100.00
3657.48	0.00	100.00
4278.42	0.00	100.00
5004.77	0.00	100.00
5854.44	0.00	100.00
6848.35	0.00	100.00
8011.01	0.00	100.00
9371.05	0.00	100.00
10961.99	0.00	100.00
12823.02	0.00	100.00
15000.00	0.00	100.00



典型值	粒径(d.nm)
D10	67.62
D20	75.14
D30	81.25
D40	87.51
D50	94.01
D60	100.99
D70	110.08
D80	121.42
D90	138.92
D100	297.55