


D50=20.5+_1.0

Date: 09/02/23 Meas #:N/A
Time: 16:19 Pres #: N/A

HENAN YALONG SUPERHARO MATERIALS CO;LTD
16-5A NO.43 ZHONGYUAN WEST ROAD
ZHENG ZHOU P.C.450007 CHINA
TEL:86-371-67650359
FAX:86-371-67650319

Summary		Percentiles	
mv = 22.16	5% = 14.92	60% = 22.39	
mn = 18.75	10% = 16.14	70% = 23.84	
ma = 20.88	30% = 18.96	80% = 25.75	
cs = 0.287	40% = 20.05	90% = 29.09	
sd = 4.825	50% = 21.16	95% = 32.72	

Dia	Vol%	Width
21.16	100%	9.650



SIZE	%PASS	%CHAN	SIZE	%PASS	%CHAN	SIZE	%PASS	%CHAN	SIZE	%PASS	%CHAN
704.0	100.00	0.00	80.70	100.00	0.00	9.250	0.00	0.00	1.060	0.00	0.00
645.6	100.00	0.00	74.00	100.00	0.00	8.482	0.00	0.00	0.972	0.00	0.00
592.0	100.00	0.00	67.86	100.00	0.00	7.778	0.00	0.00	0.892	0.00	0.00
542.9	100.00	0.00	62.23	100.00	0.12	7.133	0.00	0.00	0.818	0.00	0.00
497.8	100.00	0.00	57.06	99.88	0.19	6.541	0.00	0.00	0.750	0.00	0.00
456.5	100.00	0.00	52.33	99.69	0.26	5.998	0.00	0.00	0.688	0.00	0.00
418.6	100.00	0.00	47.98	99.43	0.38	5.500	0.00	0.00	0.630	0.00	0.00
383.9	100.00	0.00	44.00	99.05	0.59	5.044	0.00	0.00	0.578	0.00	0.00
352.0	100.00	0.00	40.35	98.46	0.95	4.625	0.00	0.00	0.530	0.00	0.00
322.8	100.00	0.00	37.00	97.51	1.54	4.241	0.00	0.00	0.486	0.00	0.00
296.0	100.00	0.00	33.93	95.97	2.66	3.889	0.00	0.00	0.446	0.00	0.00
271.4	100.00	0.00	31.11	93.31	4.40	3.566	0.00	0.00	0.409	0.00	0.00
248.9	100.00	0.00	28.53	88.91	7.07	3.270	0.00	0.00	0.375	0.00	0.00
228.2	100.00	0.00	26.16	81.84	10.88	2.999	0.00	0.00	0.344	0.00	0.00
209.3	100.00	0.00	23.99	70.96	13.83	2.750	0.00	0.00	0.315	0.00	0.00
191.9	100.00	0.00	22.00	57.13	16.02	2.522	0.00	0.00	0.289	0.00	0.00
176.0	100.00	0.00	20.17	41.11	15.14	2.312	0.00	0.00	0.265	0.00	0.00
161.4	100.00	0.00	18.50	25.97	11.23	2.121	0.00	0.00	0.243	0.00	0.00
148.0	100.00	0.00	16.96	14.74	7.54	1.945	0.00	0.00	0.223	0.00	0.00
135.7	100.00	0.00	15.56	7.20	3.83	1.783	0.00	0.00	0.204	0.00	0.00
124.5	100.00	0.00	14.27	3.37	1.78	1.635	0.00	0.00	0.187	0.00	0.00
114.1	100.00	0.00	13.08	1.59	0.86	1.499	0.00	0.00	0.172	0.00	0.00
104.7	100.00	0.00	12.00	0.73	0.39	1.375	0.00	0.00	0.158	0.00	0.00
95.96	100.00	0.00	11.00	0.34	0.22	1.261	0.00	0.00	0.145	0.00	0.00
88.00	100.00	0.00	10.09	0.12	0.12	1.156	0.00	0.00	0.133	0.00	0.00

Distribution: Volume	RunTime: 10 seconds	Fluid: Water
Progression: Geometric Root8	Run Number 1 of 1 runs	Fluid Refractive Index: 1.33
Upper Edge: 704.0	Particle: W 0.5	Loading Factor: 0.0540
Lower Edge: 0.122	Particle Transparency: Trans	Transmission: 0.97
Residuals: Disabled	Particle Refractive Index: 2.41	Above Residual: 0.00
Number Of Channels: 100	Particle Shape: Irregular	Below Residual: 0.00
X100 Extended Range: No	Database Path: N/A	Efficiency Shift: -4.00
Filter: On		Function Shift: 2.02