



百特纳米粒度电位分析仪

体积分布报告页

V4.00

: M6563-66-2	: YP
SOP : manual.sop	: 2024/3/27
: Z-	: 16:02


: 25 °C	: 1.59	: 90 °	: 23
: 0.8936 mPa.s(cP)	: 0.01	: 261.98 kcps	: 4
: 1.33	: 671 nm	: 120 s	: PS
			: 5 mm

测试结果		(d.nm)	(%)	(nm)	CV (%)	
Z-	140.46 nm	1	106.68	100.00	35.50	33.27
PDI	0.168	2				
	0.94	3				

(d.nm)	(%)	(%)
0.30	0.00	0.00
0.35	0.00	0.00
0.41	0.00	0.00
0.48	0.00	0.00
0.56	0.00	0.00
0.66	0.00	0.00
0.77	0.00	0.00
0.90	0.00	0.00
1.05	0.00	0.00
1.23	0.00	0.00
1.44	0.00	0.00
1.68	0.00	0.00
1.97	0.00	0.00
2.30	0.00	0.00
2.69	0.00	0.00
3.15	0.00	0.00
3.69	0.00	0.00
4.31	0.00	0.00
5.05	0.00	0.00
5.90	0.00	0.00
6.90	0.00	0.00
8.08	0.00	0.00
9.45	0.00	0.00
11.05	0.00	0.00

(d.nm)	(%)	(%)
12.93	0.00	0.00
15.12	0.00	0.00
17.69	0.00	0.00
20.69	0.00	0.00
24.21	0.00	0.00
28.32	0.00	0.00
33.12	0.00	0.00
38.75	0.00	0.00
45.33	0.00	0.00
53.02	0.46	0.46
62.02	6.29	6.75
72.55	14.33	21.08
84.87	19.48	40.56
99.28	19.74	60.30
116.13	16.23	76.53
135.85	11.26	87.80
158.91	6.70	94.49
185.89	3.41	97.90
217.45	1.46	99.36
254.37	0.50	99.86
297.55	0.13	99.98
348.07	0.02	100.00
407.16	0.00	100.00
476.29	0.00	100.00

(d.nm)	(%)	(%)
557.15	0.00	100.00
651.73	0.00	100.00
762.38	0.00	100.00
891.81	0.00	100.00
1043.22	0.00	100.00
1220.32	0.00	100.00
1427.50	0.00	100.00
1669.85	0.00	100.00
1953.34	0.00	100.00
2284.96	0.00	100.00
2672.88	0.00	100.00
3126.66	0.00	100.00
3657.48	0.00	100.00
4278.42	0.00	100.00
5004.77	0.00	100.00
5854.44	0.00	100.00
6848.35	0.00	100.00
8011.01	0.00	100.00
9371.05	0.00	100.00
10961.99	0.00	100.00
12823.02	0.00	100.00
15000.00	0.00	100.00



	(d.nm)
D10	64.41
D20	71.76
D30	78.20
D40	84.52
D50	91.76
D60	99.06
D70	109.35
D80	122.20
D90	143.44
D100	348.07