


D50:5.64+0.3

Date: 01/12/24 Meas #: N/A  
Time: 16:45 Pres #: N/A

HENAN YALONG SUPERHARO MATERIALS CO;LTD  
16-5A NO.43 ZHONGYUAN WEST ROAD  
ZHENG ZHOU P.C.450007 CHINA  
TEL:86-371-67650359  
FAX:86-371-67650319

Summary		Percentiles			Dia	Vol%	Width
mv = 5.905	5% = 4.036	60% = 5.974			5.656	100%	2.488
mn = 5.084	10% = 4.352	70% = 6.345					
ma = 5.592	30% = 5.068	80% = 6.836					
cs = 1.073	40% = 5.358	90% = 7.693					
sd = 1.244	50% = 5.656	95% = 8.607					



SIZE	%PASS	%CHAN	SIZE	%PASS	%CHAN	SIZE	%PASS	%CHAN	SIZE	%PASS	%CHAN
704.0	100.00	0.00	80.70	100.00	0.00	9.250	96.78	2.19	1.060	0.00	0.00
645.6	100.00	0.00	74.00	100.00	0.00	8.482	94.59	3.85	0.972	0.00	0.00
592.0	100.00	0.00	67.86	100.00	0.00	7.778	90.74	6.44	0.892	0.00	0.00
542.9	100.00	0.00	62.23	100.00	0.00	7.133	84.30	9.70	0.818	0.00	0.00
497.8	100.00	0.00	57.06	100.00	0.00	6.541	74.60	13.86	0.750	0.00	0.00
456.5	100.00	0.00	52.33	100.00	0.00	5.998	60.74	15.85	0.688	0.00	0.00
418.6	100.00	0.00	47.98	100.00	0.00	5.500	44.89	15.73	0.630	0.00	0.00
383.9	100.00	0.00	44.00	100.00	0.00	5.044	29.16	13.14	0.578	0.00	0.00
352.0	100.00	0.00	40.35	100.00	0.00	4.625	16.02	8.10	0.530	0.00	0.00
322.8	100.00	0.00	37.00	100.00	0.00	4.241	7.92	4.59	0.486	0.00	0.00
296.0	100.00	0.00	33.93	100.00	0.00	3.889	3.33	2.05	0.446	0.00	0.00
271.4	100.00	0.00	31.11	100.00	0.00	3.566	1.28	0.79	0.409	0.00	0.00
248.9	100.00	0.00	28.53	100.00	0.00	3.270	0.49	0.36	0.375	0.00	0.00
228.2	100.00	0.00	26.16	100.00	0.00	2.999	0.13	0.13	0.344	0.00	0.00
209.3	100.00	0.00	23.99	100.00	0.00	2.750	0.00	0.00	0.315	0.00	0.00
191.9	100.00	0.00	22.00	100.00	0.00	2.522	0.00	0.00	0.289	0.00	0.00
176.0	100.00	0.00	20.17	100.00	0.00	2.312	0.00	0.00	0.265	0.00	0.00
161.4	100.00	0.00	18.50	100.00	0.00	2.121	0.00	0.00	0.243	0.00	0.00
148.0	100.00	0.00	16.96	100.00	0.00	1.945	0.00	0.00	0.223	0.00	0.00
135.7	100.00	0.00	15.56	100.00	0.14	1.783	0.00	0.00	0.204	0.00	0.00
124.5	100.00	0.00	14.27	99.86	0.23	1.635	0.00	0.00	0.187	0.00	0.00
114.1	100.00	0.00	13.08	99.63	0.32	1.499	0.00	0.00	0.172	0.00	0.00
104.7	100.00	0.00	12.00	99.31	0.47	1.375	0.00	0.00	0.158	0.00	0.00
95.96	100.00	0.00	11.00	98.84	0.76	1.261	0.00	0.00	0.145	0.00	0.00
88.00	100.00	0.00	10.09	98.08	1.30	1.156	0.00	0.00	0.133	0.00	0.00

Distribution: Volume	RunTime: 10 seconds	Fluid: Water
Progression: Geometric Root8	Run Number 1 of 1 runs	Fluid Refractive Index: 1.33
Upper Edge: 704.0	Particle: W 0.5	Loading Factor: 0.0302
Lower Edge: 0.122	Particle Transparency: Trans	Transmission: 0.95
Residuals: Disabled	Particle Refractive Index: 2.41	Above Residual: 0.00
Number Of Channels: 100	Particle Shape: Irregular	Below Residual: 0.00
X100 Extended Range: No		
Filter: On	Database Path: N/A	Efficiency Shift: -4.00
		Function Shift: 2.02