


D50:9.2+0.8u

Date: 12/28/23 Meas #:N/A  
Time: 11:41 Pres #: N/A

HENAN YALONG SUPERHARO MATERIALS CO;LTD  
16-5A NO.43 ZHONGYUAN WEST ROAD  
ZHENG ZHOU P.C.450007 CHINA  
TEL:86-371-67650359  
FAX:86-371-67650319

Summary		Percentiles			Dia	Vol%	Width
mv = 9.909		5% = 6.422	60% = 10.03		9.428	100%	4.732
mn = 8.161		10% = 7.001	70% = 10.74				
ma = 9.254		30% = 8.340	80% = 11.70				
cs = 0.648		40% = 8.875	90% = 13.33				
sd = 2.366		50% = 9.428	95% = 15.09				



SIZE	%PASS	%CHAN	SIZE	%PASS	%CHAN	SIZE	%PASS	%CHAN	SIZE	%PASS	%CHAN
704.0	100.00	0.00	80.70	100.00	0.00	9.250	46.90	14.29	1.060	0.00	0.00
645.6	100.00	0.00	74.00	100.00	0.00	8.482	32.61	12.50	0.972	0.00	0.00
592.0	100.00	0.00	67.86	100.00	0.00	7.778	20.11	8.74	0.892	0.00	0.00
542.9	100.00	0.00	62.23	100.00	0.00	7.133	11.37	5.63	0.818	0.00	0.00
497.8	100.00	0.00	57.06	100.00	0.00	6.541	5.74	2.95	0.750	0.00	0.00
456.5	100.00	0.00	52.33	100.00	0.00	5.998	2.79	1.42	0.688	0.00	0.00
418.6	100.00	0.00	47.98	100.00	0.00	5.500	1.37	0.71	0.630	0.00	0.00
383.9	100.00	0.00	44.00	100.00	0.00	5.044	0.66	0.35	0.578	0.00	0.00
352.0	100.00	0.00	40.35	100.00	0.00	4.625	0.31	0.20	0.530	0.00	0.00
322.8	100.00	0.00	37.00	100.00	0.00	4.241	0.11	0.11	0.486	0.00	0.00
296.0	100.00	0.00	33.93	100.00	0.00	3.889	0.00	0.00	0.446	0.00	0.00
271.4	100.00	0.00	31.11	100.00	0.00	3.566	0.00	0.00	0.409	0.00	0.00
248.9	100.00	0.00	28.53	100.00	0.00	3.270	0.00	0.00	0.375	0.00	0.00
228.2	100.00	0.00	26.16	100.00	0.16	2.999	0.00	0.00	0.344	0.00	0.00
209.3	100.00	0.00	23.99	99.84	0.29	2.750	0.00	0.00	0.315	0.00	0.00
191.9	100.00	0.00	22.00	99.55	0.41	2.522	0.00	0.00	0.289	0.00	0.00
176.0	100.00	0.00	20.17	99.14	0.63	2.312	0.00	0.00	0.265	0.00	0.00
161.4	100.00	0.00	18.50	98.51	1.02	2.121	0.00	0.00	0.243	0.00	0.00
148.0	100.00	0.00	16.96	97.49	1.65	1.945	0.00	0.00	0.223	0.00	0.00
135.7	100.00	0.00	15.56	95.84	2.64	1.783	0.00	0.00	0.204	0.00	0.00
124.5	100.00	0.00	14.27	93.20	4.22	1.635	0.00	0.00	0.187	0.00	0.00
114.1	100.00	0.00	13.08	88.98	6.50	1.499	0.00	0.00	0.172	0.00	0.00
104.7	100.00	0.00	12.00	82.48	9.18	1.375	0.00	0.00	0.158	0.00	0.00
95.96	100.00	0.00	11.00	73.30	12.35	1.261	0.00	0.00	0.145	0.00	0.00
88.00	100.00	0.00	10.09	60.95	14.05	1.156	0.00	0.00	0.133	0.00	0.00

Distribution: Volume	RunTime: 10 seconds	Fluid: Water
Progression: Geometric Root8	Run Number 1 of 1 runs	Fluid Refractive Index: 1.33
Upper Edge: 704.0	Particle: W 0.5	Loading Factor: 0.0338
Lower Edge: 0.122	Particle Transparency: Trans	Transmission: 0.96
Residuals: Disabled	Particle Refractive Index: 2.41	Above Residual: 0.00
Number Of Channels: 100	Particle Shape: Irregular	Below Residual: 0.00
X100 Extended Range: No	Database Path: N/A	Efficiency Shift: -4.00
Filter: On		Function Shift: 2.02