


D50=13.4+ \_0.80 Date: 01/13/22 Meas #:N/A  
 Time: 11:34 Pres #: N/A

HENAN YALONG SUPERHARO MATERIALS CO;LTD  
 16-5A NO.43 ZHONGYUAN WEST ROAD  
 ZHENG ZHOU P.C.450007 CHINA  
 TEL:86-371-67650359  
 FAX:86-371-67650319

Summary		Percentiles			Dia	Vol%	Width
mv = 14.15	5% = 9.100	60% = 14.32		13.42	100%	6.976	
mn = 11.67	10% = 9.895	70% = 15.37					
ma = 13.19	30% = 11.82	80% = 16.79					
cs = 0.455	40% = 12.61	90% = 19.18					
sd = 3.488	50% = 13.42	95% = 21.73					



SIZE	%PASS	%CHAN	SIZE	%PASS	%CHAN	SIZE	%PASS	%CHAN	SIZE	%PASS	%CHAN
704.0	100.00	0.00	80.70	100.00	0.00	9.250	5.69	3.09	1.060	0.00	0.00
645.6	100.00	0.00	74.00	100.00	0.00	8.482	2.60	1.52	0.972	0.00	0.00
592.0	100.00	0.00	67.86	100.00	0.00	7.778	1.08	0.77	0.892	0.00	0.00
542.9	100.00	0.00	62.23	100.00	0.00	7.133	0.31	0.31	0.818	0.00	0.00
497.8	100.00	0.00	57.06	100.00	0.00	6.541	0.00	0.00	0.750	0.00	0.00
456.5	100.00	0.00	52.33	100.00	0.00	5.998	0.00	0.00	0.688	0.00	0.00
418.6	100.00	0.00	47.98	100.00	0.00	5.500	0.00	0.00	0.630	0.00	0.00
383.9	100.00	0.00	44.00	100.00	0.00	5.044	0.00	0.00	0.578	0.00	0.00
352.0	100.00	0.00	40.35	100.00	0.00	4.625	0.00	0.00	0.530	0.00	0.00
322.8	100.00	0.00	37.00	100.00	0.19	4.241	0.00	0.00	0.486	0.00	0.00
296.0	100.00	0.00	33.93	99.81	0.32	3.889	0.00	0.00	0.446	0.00	0.00
271.4	100.00	0.00	31.11	99.49	0.45	3.566	0.00	0.00	0.409	0.00	0.00
248.9	100.00	0.00	28.53	99.04	0.71	3.270	0.00	0.00	0.375	0.00	0.00
228.2	100.00	0.00	26.16	98.33	1.13	2.999	0.00	0.00	0.344	0.00	0.00
209.3	100.00	0.00	23.99	97.20	1.83	2.750	0.00	0.00	0.315	0.00	0.00
191.9	100.00	0.00	22.00	95.37	2.92	2.522	0.00	0.00	0.289	0.00	0.00
176.0	100.00	0.00	20.17	92.45	4.55	2.312	0.00	0.00	0.265	0.00	0.00
161.4	100.00	0.00	18.50	87.90	6.85	2.121	0.00	0.00	0.243	0.00	0.00
148.0	100.00	0.00	16.96	81.05	9.37	1.945	0.00	0.00	0.223	0.00	0.00
135.7	100.00	0.00	15.56	71.68	12.15	1.783	0.00	0.00	0.204	0.00	0.00
124.5	100.00	0.00	14.27	59.53	13.59	1.635	0.00	0.00	0.187	0.00	0.00
114.1	100.00	0.00	13.08	45.94	13.72	1.499	0.00	0.00	0.172	0.00	0.00
104.7	100.00	0.00	12.00	32.22	12.06	1.375	0.00	0.00	0.158	0.00	0.00
95.96	100.00	0.00	11.00	20.16	8.70	1.261	0.00	0.00	0.145	0.00	0.00
88.00	100.00	0.00	10.09	11.46	5.77	1.156	0.00	0.00	0.133	0.00	0.00

Distribution: Volume	RunTime: 10 seconds	Fluid: Water
Progression: Geometric Root8	Run Number 1 of 1 runs	Fluid Refractive Index: 1.33
Upper Edge: 704.0	Particle: W 0.5	Loading Factor: 0.0463
Lower Edge: 0.122	Particle Transparency: Trans	Transmission: 0.96
Residuals: Disabled	Particle Refractive Index: 2.41	Above Residual: 0.00
Number Of Channels: 100	Particle Shape: Irregular	Below Residual: 0.00
X100 Extended Range: No		
Filter: On	Database Path: N/A	