


D50=4.92+_{-0.3} Date: 10/17/23 Meas #: N/A
 Time: 11:55 Pres #: N/A

HENAN YALONG SUPERHARO MATERIALS CO;LTD
 16-5A NO.43 ZHONGYUAN WEST ROAD
 ZHENG ZHOU P.C.450007 CHINA
 TEL:86-371-67650359
 FAX:86-371-67650319

Summary		Percentiles			Dia	Vol%	Width
mv = 5.263	5% = 3.459	60% = 5.287		4.986	100%	2.427	
mn = 4.395	10% = 3.760	70% = 5.654					
ma = 4.922	30% = 4.428	80% = 6.156					
cs = 1.219	40% = 4.706	90% = 7.020					
sd = 1.213	50% = 4.986	95% = 8.000					



SIZE	%PASS	%CHAN	SIZE	%PASS	%CHAN	SIZE	%PASS	%CHAN	SIZE	%PASS	%CHAN
704.0	100.00	0.00	80.70	100.00	0.00	9.250	97.65	1.30	1.060	0.00	0.00
645.6	100.00	0.00	74.00	100.00	0.00	8.482	96.35	2.11	0.972	0.00	0.00
592.0	100.00	0.00	67.86	100.00	0.00	7.778	94.24	3.36	0.892	0.00	0.00
542.9	100.00	0.00	62.23	100.00	0.00	7.133	90.88	5.34	0.818	0.00	0.00
497.8	100.00	0.00	57.06	100.00	0.00	6.541	85.54	8.18	0.750	0.00	0.00
456.5	100.00	0.00	52.33	100.00	0.00	5.998	77.36	11.10	0.688	0.00	0.00
418.6	100.00	0.00	47.98	100.00	0.00	5.500	66.26	14.21	0.630	0.00	0.00
383.9	100.00	0.00	44.00	100.00	0.00	5.044	52.05	15.00	0.578	0.00	0.00
352.0	100.00	0.00	40.35	100.00	0.00	4.625	37.05	13.53	0.530	0.00	0.00
322.8	100.00	0.00	37.00	100.00	0.00	4.241	23.52	10.67	0.486	0.00	0.00
296.0	100.00	0.00	33.93	100.00	0.00	3.889	12.85	6.40	0.446	0.00	0.00
271.4	100.00	0.00	31.11	100.00	0.00	3.566	6.45	3.55	0.409	0.00	0.00
248.9	100.00	0.00	28.53	100.00	0.00	3.270	2.90	1.68	0.375	0.00	0.00
228.2	100.00	0.00	26.16	100.00	0.00	2.999	1.22	0.71	0.344	0.00	0.00
209.3	100.00	0.00	23.99	100.00	0.00	2.750	0.51	0.36	0.315	0.00	0.00
191.9	100.00	0.00	22.00	100.00	0.00	2.522	0.15	0.15	0.289	0.00	0.00
176.0	100.00	0.00	20.17	100.00	0.00	2.312	0.00	0.00	0.265	0.00	0.00
161.4	100.00	0.00	18.50	100.00	0.00	2.121	0.00	0.00	0.243	0.00	0.00
148.0	100.00	0.00	16.96	100.00	0.00	1.945	0.00	0.00	0.223	0.00	0.00
135.7	100.00	0.00	15.56	100.00	0.13	1.783	0.00	0.00	0.204	0.00	0.00
124.5	100.00	0.00	14.27	99.87	0.21	1.635	0.00	0.00	0.187	0.00	0.00
114.1	100.00	0.00	13.08	99.66	0.26	1.499	0.00	0.00	0.172	0.00	0.00
104.7	100.00	0.00	12.00	99.40	0.37	1.375	0.00	0.00	0.158	0.00	0.00
95.96	100.00	0.00	11.00	99.03	0.55	1.261	0.00	0.00	0.145	0.00	0.00
88.00	100.00	0.00	10.09	98.48	0.83	1.156	0.00	0.00	0.133	0.00	0.00

Distribution: Volume	RunTime: 10 seconds	Fluid: Water
Progression: Geometric Root8	Run Number 1 of 1 runs	Fluid Refractive Index: 1.33
Upper Edge: 704.0	Particle: W 0.5	Loading Factor: 0.0361
Lower Edge: 0.122	Particle Transparency: Trans	Transmission: 0.94
Residuals: Disabled	Particle Refractive Index: 2.41	Above Residual: 0.00
Number Of Channels: 100	Particle Shape: Irregular	Below Residual: 0.00
X100 Extended Range: No		
Filter: On	Database Path: N/A	Efficiency Shift: -4.00
		Function Shift: 2.02