


D50=16.00+_1.00 Date: 12/12/22 Meas #: N/A
 Time: 09:50 Pres #: N/A

HENAN YALONG SUPERHARO MATERIALS CO;LTD
 16-5A NO.43 ZHONGYUAN WEST ROAD
 ZHENG ZHOU P.C.450007 CHINA
 TEL:86-371-67650359
 FAX:86-371-67650319

Summary		Percentiles			Dia Vol% Width		
mv = 17.04	5% = 11.20	60% = 17.37	16.40	100%	7.716		
mn = 14.33	10% = 12.24	70% = 18.48					
ma = 16.04	30% = 14.55	80% = 20.01					
cs = 0.374	40% = 15.48	90% = 22.48					
sd = 3.858	50% = 16.40	95% = 25.03					



SIZE	%PASS	%CHAN	SIZE	%PASS	%CHAN	SIZE	%PASS	%CHAN	SIZE	%PASS	%CHAN
704.0	100.00	0.00	80.70	100.00	0.00	9.250	0.87	0.60	1.060	0.00	0.00
645.6	100.00	0.00	74.00	100.00	0.00	8.482	0.27	0.27	0.972	0.00	0.00
592.0	100.00	0.00	67.86	100.00	0.00	7.778	0.00	0.00	0.892	0.00	0.00
542.9	100.00	0.00	62.23	100.00	0.00	7.133	0.00	0.00	0.818	0.00	0.00
497.8	100.00	0.00	57.06	100.00	0.00	6.541	0.00	0.00	0.750	0.00	0.00
456.5	100.00	0.00	52.33	100.00	0.00	5.998	0.00	0.00	0.688	0.00	0.00
418.6	100.00	0.00	47.98	100.00	0.00	5.500	0.00	0.00	0.630	0.00	0.00
383.9	100.00	0.00	44.00	100.00	0.13	5.044	0.00	0.00	0.578	0.00	0.00
352.0	100.00	0.00	40.35	99.87	0.23	4.625	0.00	0.00	0.530	0.00	0.00
322.8	100.00	0.00	37.00	99.64	0.33	4.241	0.00	0.00	0.486	0.00	0.00
296.0	100.00	0.00	33.93	99.31	0.54	3.889	0.00	0.00	0.446	0.00	0.00
271.4	100.00	0.00	31.11	98.77	0.90	3.566	0.00	0.00	0.409	0.00	0.00
248.9	100.00	0.00	28.53	97.87	1.62	3.270	0.00	0.00	0.375	0.00	0.00
228.2	100.00	0.00	26.16	96.25	2.80	2.999	0.00	0.00	0.344	0.00	0.00
209.3	100.00	0.00	23.99	93.45	4.78	2.750	0.00	0.00	0.315	0.00	0.00
191.9	100.00	0.00	22.00	88.67	7.73	2.522	0.00	0.00	0.289	0.00	0.00
176.0	100.00	0.00	20.17	80.94	10.80	2.312	0.00	0.00	0.265	0.00	0.00
161.4	100.00	0.00	18.50	70.14	14.11	2.121	0.00	0.00	0.243	0.00	0.00
148.0	100.00	0.00	16.96	56.03	15.14	1.945	0.00	0.00	0.223	0.00	0.00
135.7	100.00	0.00	15.56	40.89	13.88	1.783	0.00	0.00	0.204	0.00	0.00
124.5	100.00	0.00	14.27	27.01	11.24	1.635	0.00	0.00	0.187	0.00	0.00
114.1	100.00	0.00	13.08	15.77	7.21	1.499	0.00	0.00	0.172	0.00	0.00
104.7	100.00	0.00	12.00	8.56	4.33	1.375	0.00	0.00	0.158	0.00	0.00
95.96	100.00	0.00	11.00	4.23	2.26	1.261	0.00	0.00	0.145	0.00	0.00
88.00	100.00	0.00	10.09	1.97	1.10	1.156	0.00	0.00	0.133	0.00	0.00

Distribution: Volume	RunTime: 10 seconds	Fluid: Water
Progression: Geometric Root8	Run Number 1 of 1 runs	Fluid Refractive Index: 1.33
Upper Edge: 704.0	Particle: W 0.5	Loading Factor: 0.0514
Lower Edge: 0.122	Particle Transparency: Trans	Transmission: 0.97
Residuals: Disabled	Particle Refractive Index: 2.41	Above Residual: 0.00
Number Of Channels: 100	Particle Shape: Irregular	Below Residual: 0.00
X100 Extended Range: No		
Filter: On	Database Path: N/A	Efficiency Shift: -4.00
		Function Shift: 2.02