



百特纳米粒度电位分析仪

体积分布报告页

V4.00

: M6563-34-2	: YP
SOP : manual.sop	: 2024/3/26
: Z-	: 15:07


: 90 °	: 14
: 25 °C	: 1.59
: 0.8936 mPa.s(cP)	: 0.01
: 1.33	: 671 nm
: 408.55 kcps	: 4
:	: PS
: 120 s	: 5 mm

测试结果		(d.nm)	(%)	(nm)	CV (%)	
Z-	134.98 nm	1	101.39	100.00	34.54	34.06
PDI	0.072	2				
	0.90	3				

(d.nm)	(%)	(%)
0.30	0.00	0.00
0.35	0.00	0.00
0.41	0.00	0.00
0.48	0.00	0.00
0.56	0.00	0.00
0.66	0.00	0.00
0.77	0.00	0.00
0.90	0.00	0.00
1.05	0.00	0.00
1.23	0.00	0.00
1.44	0.00	0.00
1.68	0.00	0.00
1.97	0.00	0.00
2.30	0.00	0.00
2.69	0.00	0.00
3.15	0.00	0.00
3.69	0.00	0.00
4.31	0.00	0.00
5.05	0.00	0.00
5.90	0.00	0.00
6.90	0.00	0.00
8.08	0.00	0.00
9.45	0.00	0.00
11.05	0.00	0.00

(d.nm)	(%)	(%)
12.93	0.00	0.00
15.12	0.00	0.00
17.69	0.00	0.00
20.69	0.00	0.00
24.21	0.00	0.00
28.32	0.00	0.00
33.12	0.00	0.00
38.75	0.00	0.00
45.33	0.00	0.00
53.02	2.44	2.44
62.02	9.12	11.56
72.55	16.17	27.73
84.87	19.62	47.35
99.28	18.55	65.89
116.13	14.52	80.42
135.85	9.69	90.11
158.91	5.56	95.67
185.89	2.73	98.40
217.45	1.13	99.53
254.37	0.37	99.90
297.55	0.09	99.99
348.07	0.01	100.00
407.16	0.00	100.00
476.29	0.00	100.00

(d.nm)	(%)	(%)
557.15	0.00	100.00
651.73	0.00	100.00
762.38	0.00	100.00
891.81	0.00	100.00
1043.22	0.00	100.00
1220.32	0.00	100.00
1427.50	0.00	100.00
1669.85	0.00	100.00
1953.34	0.00	100.00
2284.96	0.00	100.00
2672.88	0.00	100.00
3126.66	0.00	100.00
3657.48	0.00	100.00
4278.42	0.00	100.00
5004.77	0.00	100.00
5854.44	0.00	100.00
6848.35	0.00	100.00
8011.01	0.00	100.00
9371.05	0.00	100.00
10961.99	0.00	100.00
12823.02	0.00	100.00
15000.00	0.00	100.00



	(d.nm)
D10	60.49
D20	67.52
D30	73.98
D40	80.26
D50	86.93
D60	94.70
D70	104.04
D80	115.65
D90	135.64
D100	348.07