


D50=2.38+0.2u

Date: 09/13/23 Meas #:N/A
Time: 09:14 Pres #: N/A

HENAN YALONG SUPERHARO MATERIALS CO;LTD
16-5A NO.43 ZHONGYUAN WEST ROAD
ZHENG ZHOU P.C.450007 CHINA
TEL:86-371-67650359
FAX:86-371-67650319

Summary		Percentiles			Dia	Vol%	Width
mv = 2.533		5% = 1.525	60% = 2.579		2.424	100%	1.247
mn = 1.931		10% = 1.731	70% = 2.757				
ma = 2.328		30% = 2.130	80% = 3.001				
cs = 2.578		40% = 2.277	90% = 3.413				
sd = 0.624		50% = 2.424	95% = 3.885				



SIZE	%PASS	%CHAN	SIZE	%PASS	%CHAN	SIZE	%PASS	%CHAN	SIZE	%PASS	%CHAN
704.0	100.00	0.00	80.70	100.00	0.00	9.250	100.00	0.00	1.060	0.80	0.35
645.6	100.00	0.00	74.00	100.00	0.00	8.482	100.00	0.00	0.972	0.45	0.28
592.0	100.00	0.00	67.86	100.00	0.00	7.778	100.00	0.13	0.892	0.17	0.17
542.9	100.00	0.00	62.23	100.00	0.00	7.133	99.87	0.20	0.818	0.00	0.00
497.8	100.00	0.00	57.06	100.00	0.00	6.541	99.67	0.24	0.750	0.00	0.00
456.5	100.00	0.00	52.33	100.00	0.00	5.998	99.43	0.33	0.688	0.00	0.00
418.6	100.00	0.00	47.98	100.00	0.00	5.500	99.10	0.47	0.630	0.00	0.00
383.9	100.00	0.00	44.00	100.00	0.00	5.044	98.63	0.71	0.578	0.00	0.00
352.0	100.00	0.00	40.35	100.00	0.00	4.625	97.92	1.09	0.530	0.00	0.00
322.8	100.00	0.00	37.00	100.00	0.00	4.241	96.83	1.80	0.486	0.00	0.00
296.0	100.00	0.00	33.93	100.00	0.00	3.889	95.03	2.91	0.446	0.00	0.00
271.4	100.00	0.00	31.11	100.00	0.00	3.566	92.12	4.75	0.409	0.00	0.00
248.9	100.00	0.00	28.53	100.00	0.00	3.270	87.37	7.44	0.375	0.00	0.00
228.2	100.00	0.00	26.16	100.00	0.00	2.999	79.93	10.23	0.344	0.00	0.00
209.3	100.00	0.00	23.99	100.00	0.00	2.750	69.70	13.22	0.315	0.00	0.00
191.9	100.00	0.00	22.00	100.00	0.00	2.522	56.48	14.12	0.289	0.00	0.00
176.0	100.00	0.00	20.17	100.00	0.00	2.312	42.36	12.95	0.265	0.00	0.00
161.4	100.00	0.00	18.50	100.00	0.00	2.121	29.41	10.60	0.243	0.00	0.00
148.0	100.00	0.00	16.96	100.00	0.00	1.945	18.81	7.07	0.223	0.00	0.00
135.7	100.00	0.00	15.56	100.00	0.00	1.783	11.74	4.50	0.204	0.00	0.00
124.5	100.00	0.00	14.27	100.00	0.00	1.635	7.24	2.70	0.187	0.00	0.00
114.1	100.00	0.00	13.08	100.00	0.00	1.499	4.54	1.57	0.172	0.00	0.00
104.7	100.00	0.00	12.00	100.00	0.00	1.375	2.97	1.02	0.158	0.00	0.00
95.96	100.00	0.00	11.00	100.00	0.00	1.261	1.95	0.67	0.145	0.00	0.00
88.00	100.00	0.00	10.09	100.00	0.00	1.156	1.28	0.48	0.133	0.00	0.00

Distribution: Volume	RunTime: 10 seconds	Fluid: Water
Progression: Geometric Root8	Run Number 1 of 1 runs	Fluid Refractive Index: 1.33
Upper Edge: 704.0	Particle: W 0.5	Loading Factor: 0.0164
Lower Edge: 0.122	Particle Transparency: Trans	Transmission: 0.95
Residuals: Disabled	Particle Refractive Index: 2.41	Above Residual: 0.00
Number Of Channels: 100	Particle Shape: Irregular	Below Residual: 0.00
X100 Extended Range: No	Database Path: N/A	Efficiency Shift: -4.00
Filter: On		Function Shift: 2.02