


D50:20.5+_1.0 Date: 07/23/02 Meas #:N/A
 Time: 11:56 Pres #: N/A

HENAN YALONG SUPERHARO MATERIALS CO;LTD
 16-5A NO.43 ZHONGYUAN WEST ROAD
 ZHENG ZHOU P.C.450007 CHINA
 TEL:86-371-67650359
 FAX:86-371-67650319

Summary		Percentiles			Dia	Vol%	Width
mv = 21.41	5% = 14.56	60% = 21.66	80% = 24.87	20.52	100%	9.164	
mn = 18.31	10% = 15.76	70% = 23.03	90% = 27.98				
ma = 20.25	30% = 18.41	95% = 31.37					
cs = 0.296	40% = 19.47						
sd = 4.582	50% = 20.52						



SIZE	%PASS	%CHAN	SIZE	%PASS	%CHAN	SIZE	%PASS	%CHAN	SIZE	%PASS	%CHAN
704.0	100.00	0.00	80.70	100.00	0.00	9.250	0.00	0.00	1.060	0.00	0.00
645.6	100.00	0.00	74.00	100.00	0.00	8.482	0.00	0.00	0.972	0.00	0.00
592.0	100.00	0.00	67.86	100.00	0.00	7.778	0.00	0.00	0.892	0.00	0.00
542.9	100.00	0.00	62.23	100.00	0.00	7.133	0.00	0.00	0.818	0.00	0.00
497.8	100.00	0.00	57.06	100.00	0.00	6.541	0.00	0.00	0.750	0.00	0.00
456.5	100.00	0.00	52.33	100.00	0.20	5.998	0.00	0.00	0.688	0.00	0.00
418.6	100.00	0.00	47.98	99.80	0.35	5.500	0.00	0.00	0.630	0.00	0.00
383.9	100.00	0.00	44.00	99.45	0.50	5.044	0.00	0.00	0.578	0.00	0.00
352.0	100.00	0.00	40.35	98.95	0.77	4.625	0.00	0.00	0.530	0.00	0.00
322.8	100.00	0.00	37.00	98.18	1.26	4.241	0.00	0.00	0.486	0.00	0.00
296.0	100.00	0.00	33.93	96.92	2.15	3.889	0.00	0.00	0.446	0.00	0.00
271.4	100.00	0.00	31.11	94.77	3.58	3.566	0.00	0.00	0.409	0.00	0.00
248.9	100.00	0.00	28.53	91.19	5.97	3.270	0.00	0.00	0.375	0.00	0.00
228.2	100.00	0.00	26.16	85.22	9.55	2.999	0.00	0.00	0.344	0.00	0.00
209.3	100.00	0.00	23.99	75.67	12.85	2.750	0.00	0.00	0.315	0.00	0.00
191.9	100.00	0.00	22.00	62.82	16.04	2.522	0.00	0.00	0.289	0.00	0.00
176.0	100.00	0.00	20.17	46.78	16.01	2.312	0.00	0.00	0.265	0.00	0.00
161.4	100.00	0.00	18.50	30.77	12.82	2.121	0.00	0.00	0.243	0.00	0.00
148.0	100.00	0.00	16.96	17.95	9.12	1.945	0.00	0.00	0.223	0.00	0.00
135.7	100.00	0.00	15.56	8.83	4.75	1.783	0.00	0.00	0.204	0.00	0.00
124.5	100.00	0.00	14.27	4.08	2.25	1.635	0.00	0.00	0.187	0.00	0.00
114.1	100.00	0.00	13.08	1.83	1.05	1.499	0.00	0.00	0.172	0.00	0.00
104.7	100.00	0.00	12.00	0.78	0.43	1.375	0.00	0.00	0.158	0.00	0.00
95.96	100.00	0.00	11.00	0.35	0.23	1.261	0.00	0.00	0.145	0.00	0.00
88.00	100.00	0.00	10.09	0.12	0.12	1.156	0.00	0.00	0.133	0.00	0.00

Distribution: Volume	RunTime: 10 seconds	Fluid: Water
Progression: Geometric Root8	Run Number 1 of 1 runs	Fluid Refractive Index: 1.33
Upper Edge: 704.0	Particle: W 0.5	Loading Factor: 0.0308
Lower Edge: 0.122	Particle Transparency: Trans	Transmission: 0.98
Residuals: Disabled	Particle Refractive Index: 2.41	Above Residual: 0.00
Number Of Channels: 100	Particle Shape: Irregular	Below Residual: 0.00
X100 Extended Range: No		
Filter: On	Database Path: N/A	