


测量详细信息	
Sample Name	Average of '0.25 -0.5 711码'

测量详细信息	
Measurement Date Time	2020/3/27 20:19:13
Result Source	Averaged

分析	
Particle Name	Diamond
Particle Refractive Index	2.418
Particle Absorption Index	0.010
Dispersant Name	Water
Dispersant Refractive Index	1.330
Scattering Model	Mie
Analysis Model	General Purpose
Weighted Residual	0.95 %
Laser Obscuration	15.94 %

结果	
Concentration	0.0005 %
Span	1.471
Uniformity	0.448
Specific Surface Area	19470 m2/kg
D [3,2]	0.308 μm
D [4,3]	0.391 μm
Dv (10)	0.183 μm
Dv (50)	0.339 μm
Dv (90)	0.682 μm



Result											
Size (μm)	% Volume In	Size (μm)	% Volume In	Size (μm)	% Volume In	Size (μm)	% Volume In	Size (μm)	% Volume In	Size (μm)	% Volume In
0.0100	0.00	0.0876	0.00	0.767	3.01	6.72	0.00	58.9	0.00	516	0.00
0.0114	0.00	0.0995	0.25	0.872	2.06	7.64	0.00	66.9	0.00	586	0.00
0.0129	0.00	0.113	0.83	0.991	1.12	8.68	0.00	76.0	0.00	666	0.00
0.0147	0.00	0.128	1.84	1.13	0.17	9.86	0.00	86.4	0.00	756	0.00
0.0167	0.00	0.146	3.24	1.28	0.00	11.2	0.00	98.1	0.00	859	0.00
0.0189	0.00	0.166	4.91	1.45	0.00	12.7	0.00	111	0.00	976	0.00
0.0215	0.00	0.188	6.60	1.65	0.00	14.5	0.00	127	0.00	1110	0.00
0.0244	0.00	0.214	8.03	1.88	0.00	16.4	0.00	144	0.00	1260	0.00
0.0278	0.00	0.243	9.01	2.13	0.00	18.7	0.00	163	0.00	1430	0.00
0.0315	0.00	0.276	9.51	2.42	0.00	21.2	0.00	186	0.00	1630	0.00
0.0358	0.00	0.314	9.56	2.75	0.00	24.1	0.00	211	0.00	1850	0.00
0.0407	0.00	0.357	9.13	3.12	0.00	27.4	0.00	240	0.00	2100	0.00
0.0463	0.00	0.405	8.31	3.55	0.00	31.1	0.00	272	0.00	2390	0.00
0.0526	0.00	0.460	7.31	4.03	0.00	35.3	0.00	310	0.00	2710	0.00
0.0597	0.00	0.523	6.16	4.58	0.00	40.1	0.00	352	0.00	3080	0.00
0.0679	0.00	0.594	5.01	5.21	0.00	45.6	0.00	400	0.00	3500	0.00
0.0771	0.00	0.675	3.96	5.92	0.00	51.8	0.00	454	0.00		