


HENAN YALONG SUPERHARO MATERIALS CO;LTD  
 16-5A NO.43 ZHONGYUAN WEST ROAD  
 ZHENG ZHOU P.C.450007 CHINA  
 TEL:86-371-67650359  
 FAX:86-371-67650319

D50=2.38+\_0.20 Date: 01/01/02 Meas #: N/A  
 Time: 00:15 Pres #: N/A

Summary	Percentiles	Dia	Vol%	Width
mv = 2.625	5% = 1.636	60% = 2.687	2.535	100%
mn = 2.036	10% = 1.848	70% = 2.867		
ma = 2.437	30% = 2.243	80% = 3.106		
cs = 2.462	40% = 2.392	90% = 3.502		
sd = 0.616	50% = 2.535	95% = 3.927		



SIZE	%PASS	%CHAN	SIZE	%PASS	%CHAN	SIZE	%PASS	%CHAN	SIZE	%PASS	%CHAN
704.0	100.00	0.00	80.70	100.00	0.00	9.250	100.00	0.00	1.060	0.64	0.28
645.6	100.00	0.00	74.00	100.00	0.00	8.482	100.00	0.00	0.972	0.36	0.22
592.0	100.00	0.00	67.86	100.00	0.00	7.778	100.00	0.00	0.892	0.14	0.14
542.9	100.00	0.00	62.23	100.00	0.00	7.133	100.00	0.00	0.818	0.00	0.00
497.8	100.00	0.00	57.06	100.00	0.00	6.541	100.00	0.20	0.750	0.00	0.00
456.5	100.00	0.00	52.33	100.00	0.00	5.998	99.80	0.35	0.688	0.00	0.00
418.6	100.00	0.00	47.98	100.00	0.00	5.500	99.45	0.50	0.630	0.00	0.00
383.9	100.00	0.00	44.00	100.00	0.00	5.044	98.95	0.78	0.578	0.00	0.00
352.0	100.00	0.00	40.35	100.00	0.00	4.625	98.17	1.27	0.530	0.00	0.00
322.8	100.00	0.00	37.00	100.00	0.00	4.241	96.90	2.17	0.486	0.00	0.00
296.0	100.00	0.00	33.93	100.00	0.00	3.889	94.73	3.62	0.446	0.00	0.00
271.4	100.00	0.00	31.11	100.00	0.00	3.566	91.11	5.91	0.409	0.00	0.00
248.9	100.00	0.00	28.53	100.00	0.00	3.270	85.20	9.22	0.375	0.00	0.00
228.2	100.00	0.00	26.16	100.00	0.00	2.999	75.98	12.13	0.344	0.00	0.00
209.3	100.00	0.00	23.99	100.00	0.00	2.750	63.85	14.71	0.315	0.00	0.00
191.9	100.00	0.00	22.00	100.00	0.00	2.522	49.14	14.67	0.289	0.00	0.00
176.0	100.00	0.00	20.17	100.00	0.00	2.312	34.47	12.02	0.265	0.00	0.00
161.4	100.00	0.00	18.50	100.00	0.00	2.121	22.45	8.96	0.243	0.00	0.00
148.0	100.00	0.00	16.96	100.00	0.00	1.945	13.49	5.39	0.223	0.00	0.00
135.7	100.00	0.00	15.56	100.00	0.00	1.783	8.10	3.11	0.204	0.00	0.00
124.5	100.00	0.00	14.27	100.00	0.00	1.635	4.99	1.80	0.187	0.00	0.00
114.1	100.00	0.00	13.08	100.00	0.00	1.499	3.19	1.03	0.172	0.00	0.00
104.7	100.00	0.00	12.00	100.00	0.00	1.375	2.16	0.68	0.158	0.00	0.00
95.96	100.00	0.00	11.00	100.00	0.00	1.261	1.48	0.48	0.145	0.00	0.00
88.00	100.00	0.00	10.09	100.00	0.00	1.156	1.00	0.36	0.133	0.00	0.00

Distribution: Volume RunTime: 10 seconds Fluid: Water  
 Progression: Geometric Root8 Run Number 1 of 1 runs Fluid Refractive Index: 1.33  
 Upper Edge: 704.0 Particle: W 0.5 Loading Factor: 0.0138  
 Lower Edge: 0.122 Particle Transparency: Trans Transmission: 0.96  
 Residuals: Disabled Particle Refractive Index: 2.41 Above Residual: 0.00  
 Number Of Channels: 100 Particle Shape: Irregular Below Residual: 0.00  
 X100 Extended Range: No  
 Filter: On Database Path: N/A